



Adherend Thermal Effects During Bonding With Inductively Heated Films

by Eric D. Wetzel and Bruce K. Fink

ARL-TR-2461

April 2001

20010501 130

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5069

ARL-TR-2461

April 2001

Adherend Thermal Effects During Bonding With Inductively Heated Films

Eric D. Wetzel and Bruce K. Fink
Weapons and Materials Research Directorate, ARL

Approved for public release; distribution is unlimited.

Abstract

The thermal performance of an inductively heated film sandwiched between two identical adherends is investigated. Models for infinite conductivity finite thickness adherends, finite conductivity semi-infinite thickness adherends, and finite conductivity finite thickness adherends are presented. Calculations are performed for polymer-matrix composite, ceramic, and metal adherends for a variety of adherend thicknesses. The results show that for expected bonding applications, film heating rates will be reduced by a factor of 10–100, as compared with insulated film heating rates with no attached adherends. Higher reductions in heating performance are noted for ceramic and metal adherends as compared with composite adherends. However, even with the most severe reductions in heating rates, bonding with inductively heated films is feasible.

Table of Contents

	<u>Page</u>
List of Figures	v
List of Tables	vii
1. Introduction	1
1.1 Motivation	1
1.2 Approach	1
2. Bondline Heating Rate Solutions	3
2.1 Infinite Conductivity, Finite Thickness Adherend	3
2.2 Finite Conductivity, Semi-Infinite Thickness Adherend	5
2.3 Finite Conductivity, Finite Thickness Adherend	6
3. Calculations	9
3.1 Material Properties	9
3.2 Bondline Heating Rates for Specific Material Systems	12
3.2.1 <i>Infinite Conductivity Adherend</i>	12
3.2.2 <i>Semi-Infinite Thickness Adherend</i>	12
3.2.3 <i>Finite Thickness, Finite Conductivity Adherend</i>	13
4. Analysis and Conclusions	16
4.1 Model Applicability	16
4.2 Effect of Adherends on Feasibility of Bonding with Magnetic Particle Films	18
4.3 Extension of Results to Non-Symmetric Adherends	19
5. References	21
Distribution List	23
Report Documentation Page	41

INTENTIONALLY LEFT BLANK.

List of Figures

<u>Figure</u>	<u>Page</u>
1. Schematic for Film / Adherend Heat Transfer Models.	2
2. Reduced Heating Rate as a Function of H for Infinite Conductivity Adherend Solution.	5
3. Reduced Heating Rate as a Function of t/τ_i for Semi-Infinite Adherend Solution.	7
4. Reduced Heating Rate as a Function of t/τ_f and H for Finite Adherend Solution.	9
5. Reduced Heating Rate as a Function of t/τ_f and H for Finite Adherend Solution, with Superimposed Semi-Infinite Thickness Adherend Model and Infinite Conductivity Solution.	10
6. Reduced Heating Rate as a Function of Film Thickness Ratio l/L for Various Adherend Materials and Infinite Conductivity Adherend Solution.	12
7. Reduced Heating Rate as a Function of Time and Film Thickness for Various Adherend Materials and Semi-Infinite Adherend Solution.	13
8. Time to Achieve Reduced Heating Rates as a Function of Film Thickness for Various Adherend Materials and Semi-Infinite Adherend Solution.	14
9. Reduced Heating Rate as a Function of Time and Adherend Thickness for Various Adherend Materials, with 0.1 mm Film Thickness and Finite Adherend Solution.	14
10. Reduced Heating Rate as a Function of Time and Adherend Thickness for Various Adherend Materials, with 1 mm Film Thickness and Finite Adherend Solution.	15
11. Reduced Heating Rate as a Function of Time and Adherend Thickness for Various Adherend Materials, with 5 mm Film Thickness and Finite Adherend Solution.	15

INTENTIONALLY LEFT BLANK.

List of Tables

<u>Table</u>	<u>Page</u>
1. Film Component and Composite Material Properties.	11
2. Adherend Thermophysical Properties.	11
3. Adherend Characteristic Conduction Lengths.	18
4. Expected Heating Rates for 15% NiZn Ferrite / Polymer Film with Thickness 2l = 1 mm Sandwiched Between Two Identical Adherends of Various Materials.	19

INTENTIONALLY LEFT BLANK.

1. Introduction

1.1 Motivation. The need to reduce weight and improve survivability in Army vehicle and weapons systems has led to increasing usage of polymer-matrix composites and ceramic materials for structural and armor applications. These materials, however, pose major challenges for integration into complex assemblies due to limitations in joining technology. Unlike metallic structures, which can be welded or fastened mechanically, composites and ceramics require surface bonding methods such as thermoplastic hot-melt bonding or adhesives. Since each material satisfies specific performance objectives, final assemblies will often involve multiple materials. This characteristic requires that composites and ceramics will be bonded to many different materials, including metals and other composites and ceramics.

Recent efforts have shown the potential of using inductively heated films for bonding [1]. A thermoplastic or adhesive is doped with micron-sized magnetic particles. In a high frequency magnetic field, these magnetic particles heat. This thermal energy melts the thermoplastic to form a hot-melt bond, or cures the adhesive. Because the films are generally thin and the magnetic field penetrates completely into the film, heating in the film is reasonably uniform.

For magnetic particle film bonding to be feasible, the film heating rate must be sufficient to generate the time-temperature profile required for a given bonding process. Wetzel and Fink [1] have predicted heating rates for magnetic particle films as a function of magnetic field characteristics and material properties. However, these predictions assume an insulated film with no thermal losses, so that the conductive losses into the adherends are neglected.

In this report we construct models to predict the effect of the adherends on the film heating performance. Because of the range of materials and plate thicknesses which will eventually be joined using this technology, a general model is derived which can be used as a design tool for future joining scenarios. Specific calculations are also provided for a wide range of likely adherend properties, to assess the order-of-magnitude effects of adherends on bondline processing.

1.2 Approach. Our objective is to assess the changes in bond processing caused by the presence of the adherend. The most relevant metric for quantification of magnetic particulate film heating performance is the bondline heating rate [1]. To calculate this metric, heat transfer solutions are derived or cited for the case of a volumetrically heated film attached to different classes of adherends in section 2. These models are used to calculate the heating rate at the bondline. Comparing these heating rates with the heating rates predicted for an insulated film with no attached adherend provides a quantitative measure of the effect of the adherend on the




Figure 1. Schematic for Film / Adherend Heat Transfer Models.

bondline thermal processing. Such comparisons are provided for specific adherend materials and thicknesses in section 3, and a general discussion on the implications and applicability of these results is provided in section 4.

The model geometry we will use is shown in Figure 1. A volumetrically heated film of thickness l is insulated on one side and attached via a perfectly-conducting interface to a conductive adherend of thickness L . Although the film is a two-phase particulate composite, we will treat it as a uniform material with density, specific heat, conductivity, and thermal diffusivity denoted by $\hat{\rho}$, \hat{c}_p , \hat{k} , and $\hat{\alpha} \equiv \hat{k}/\hat{\rho}\hat{c}_p$, respectively. We assume that the film is sufficiently thin and conductive (small $l^2/\hat{\alpha}$) such that the temperature in the film is always uniform. More formally, we assume that $t_p \gg l^2/\hat{\alpha}$, where t_p is the process time scale. The film generates heating power per unit volume of $\bar{Q}_T \equiv Q_T/lA_x$, where A_x is the cross-sectional area of the film and Q_T is the total heating power in the film. The adherend has thermophysical properties ρ , c_p , k , and $\alpha \equiv k/\rho c_p$, and is insulated on its free face. The analysis is 1-D, so that both adherend and film are assumed to be infinite in cross-section.

The insulated film assumption can be interpreted in two ways. The most obvious interpretation is that the film is attached to a thermally insulating medium. The second interpretation is a symmetry boundary condition. If a film is placed symmetrically between two identical adherends, there is no heat flow across the sandwich centerline. Therefore our model results can be interpreted as the heating rates for a piece of film of thickness $2l$ sandwiched between two adherends composed of identical material, and each of thickness L .

Three different heat transfer models will be presented, each involving different physical assumptions. The first model (section 2.1) assumes finite adherend thickness, but infinite adherend conductivity. The temperature is assumed to be uniform in the adherend, so it only provides a lumped thermal mass in addition to that of the film itself. This solution is most

relevant to thin, highly conductive adherends or long process times. The second model (section 2.2) assumes a semi-infinite adherend thickness, and finite adherend conductivity. This solution is most relevant to thick, poorly conducting adherends or short process times. The third model (section 2.3) is the most general case, with finite adherend thickness and conductivity. The infinite conductivity and semi-infinite thickness adherend models are limiting cases of this general solution.

2. Bondline Heating Rate Solutions

In this section we present solutions for the bondline heating rates for three different adherend scenarios. Two of these solutions address limiting adherend characteristics: an adherend with infinite conductivity and finite thickness, and an adherend with finite conductivity and semi-infinite thickness. The third solution is the most general, for an adherend with finite conductivity and finite thickness.

2.1 Infinite Conductivity, Finite Thickness Adherend. To model thin, highly conductive adherends, in this section we solve for the heating rate for the case of an adherend with infinite conductivity, $k \rightarrow \infty$. In this case the temperature in both the film and adherend is uniform.

The total heating power generated in the film is

$$Q_T = \bar{Q}_T V_f = \bar{Q}_T A_x l \quad (1)$$

where V_f is the film volume. The heat capacity of the film can be written as

$$\text{film heat capacity} = \hat{\rho} \hat{c}_p V_f = \hat{\rho} \hat{c}_p A_x l \quad (2)$$

and the adherend heat capacity can be written as

$$\text{adherend heat capacity} = \rho c_p V_a = \rho c_p A_x L \quad (3)$$

Assuming uniform temperatures and heat generated only in the film, a lumped energy balance can be written as

$$\bar{Q}_T A_x l = \frac{dT}{dt} (\hat{\rho} \hat{c}_p A_x l + \rho c_p A_x L) \quad (4)$$

where T is the adherend temperature and t is time. Simplifying yields

$$\frac{\bar{Q}_T}{\hat{\rho}\hat{c}_p} = \frac{dT}{dt} \left(1 + \frac{\rho c_p L}{\hat{\rho}\hat{c}_p l} \right) \quad (5)$$

This equation can be rewritten as

$$\frac{dT}{dt} = \frac{\bar{Q}_T}{\hat{\rho}\hat{c}_p} \frac{H}{1 + H} \quad (6)$$

where

$$H \equiv \frac{\hat{\rho}\hat{c}_p l}{\rho c_p L} \quad (7)$$

Wetzel and Fink [1] calculate the expected heating rates for magnetic particle films as a function of magnetic field strength and frequency, and polymer film and magnetic particle material properties. The heating rates are derived assuming an insulated film with no attached adherend, with the result expressed as

$$\frac{dT}{dt} = \frac{\bar{Q}_T}{\hat{\rho}\hat{c}_p} \quad (8)$$

where \bar{Q}_T is determined by the specific film material system and magnetic field characteristics under consideration. For comparison with these insulated, isolated film heating rates, it will be useful to define the reduced heating rate

$$R_{\text{rate}} \equiv \frac{\text{Heating rate with adherend}}{\text{Heating rate without adherend}} \quad (9)$$

$$\equiv \frac{\text{Heating rate with adherend}}{\bar{Q}_T / \hat{\rho}\hat{c}_p} \quad (10)$$

Using equation 6, the reduced heating rate for an adherend with infinite conductivity is

$$R_{\text{rate}} = \frac{H}{1 + H} \quad (11)$$

Figure 2 shows R_{rate} as a function of H .




Figure 2. Reduced Heating Rate as a Function of H for Infinite Conductivity Adherend Solution.

2.2 Finite Conductivity, Semi-Infinite Thickness Adherend. Thick adherends can be approximately modeled by assuming a semi-infinite adherend, $L \rightarrow \infty$. The transient temperature profile in such an adherend, for the case of a perfectly-attached, thin, infinite conductivity, heat-generating film, is given by Trankle [2] (as cited in Carslaw and Jaeger [3]) as

$$T(x, t) = T_i + \frac{\bar{Q}_T}{\hat{\rho}\hat{c}_p} G \frac{l^2}{\alpha} \left[\frac{1}{\sqrt{\pi}} \frac{2\sqrt{\alpha t}}{l} e^{-\frac{x^2}{4\alpha t}} - \left(G + \frac{x}{l} \right) \operatorname{erfc} \frac{x}{2\sqrt{\alpha t}} + G e^{\left(\frac{1}{G} \frac{x}{l} + \frac{1}{G^2} \frac{\alpha t}{l^2} \right)} \operatorname{erfc} \left(\frac{x}{2\sqrt{\alpha t}} + \frac{1}{G} \frac{\sqrt{\alpha t}}{l} \right) \right] \quad (12)$$

where

$$G \equiv \frac{\hat{\rho}\hat{c}_p}{\rho c_p} \quad (13)$$

T_i is the initial, uniform temperature in the adherend, and x is the spatial coordinate in the thickness direction, with $x = 0$ at the film / adherend interface. We are only interested in the

temperature at this interface, where

$$T(0, t) = T_i(0) + \frac{l^2 \bar{Q}_T}{k} \left[\frac{1}{\sqrt{\pi}} \frac{2\sqrt{\alpha t}}{l} - G + G e^{(\frac{1}{G^2} \frac{\alpha t}{l^2})} \operatorname{erfc} \frac{1}{G} \frac{\sqrt{\alpha t}}{l} \right] \quad (14)$$

We can rewrite this equation as

$$T(0, t) = T_i(0) + \frac{l^2 \bar{Q}_T}{k} \left[\frac{1}{\sqrt{\pi}} 2G \sqrt{\frac{t}{\tau_i}} - G + G e^{(t/\tau_i)} \operatorname{erfc} \sqrt{\frac{t}{\tau_i}} \right] \quad (15)$$

where

$$\tau_i = G^2 \frac{l^2}{\alpha} \quad (16)$$

The heating rate at the film / adherend interface can be calculated by differentiating equation 15 with respect to time, giving

$$\frac{dT}{dt}(0, t) = \frac{l^2 \bar{Q}_T}{k} \frac{G}{\tau_i} e^{(t/\tau_i)} \operatorname{erfc} \sqrt{\frac{t}{\tau_i}} \quad (17)$$

Using equation 10, we can write the reduced heating rate for the case of the semi-infinite adherend as

$$R_{\text{rate}} = \frac{l^2 \hat{\rho} \hat{c}_p}{k} \frac{G}{\tau_i} e^{(t/\tau_i)} \operatorname{erfc} \sqrt{\frac{t}{\tau_i}} \quad (18)$$

or

$$R_{\text{rate}} = e^{(t/\tau_i)} \operatorname{erfc} \sqrt{\frac{t}{\tau_i}} \quad (19)$$

This equation gives the reduced heating rate for the case of a semi-infinite adherend. Figure 3 gives R_{rate} as a function of reduced time t/τ_i , as calculated through equation 19.

2.3 Finite Conductivity, Finite Thickness Adherend. The most general solution models an adherend with finite thickness L and finite conductivity k . The adherend is insulated at $x = L$, and at $x = 0$. A perfectly-attached, thin, infinite conductivity, heat-generating film is bonded to the adherend at $x = 0$, and the adherend is insulated at $x = L$.




Figure 3. Reduced Heating Rate as a Function of t/τ_i for Semi-Infinite Adherend Solution.

The transient temperature profile for this case is given by Carslaw and Jaeger [4] as

$$T(x, t) = T_i + \frac{\bar{Q}_T}{\hat{\rho}\hat{c}_p} H \tau_f \left\{ -\frac{1}{6} \frac{1+3H}{(1+H)^2} + \frac{1}{2} \frac{(1-x/L)^2}{1+H} + \frac{t/\tau_f}{1+H} - \sum_{k_n > 0} \frac{4 \cos(k_n[1-x/L])}{k_n^2 (H + H^2 k_n^2 + 1) \cos k_n} e^{-k_n^2 t/\tau_f} \right\} \quad (20)$$

where the dimensionless parameter H was defined in equation 7 and

$$\tau_f \equiv L^2/\alpha \quad (21)$$

k_n are the roots to the transcendental equation

$$\tan k_n + H k_n = 0 \quad (22)$$

For our adherend studies, we are only interested with the temperature at the film / adherend interface, $x = 0$, where

$$T(0, t) = T_i + \frac{\bar{Q}_T}{\hat{\rho}\hat{c}_p} H \tau_f \left\{ -\frac{1}{6} \frac{1+3H}{(1+H)^2} + \frac{1}{2} \frac{1}{1+H} + \frac{t/\tau_f}{1+H} - \sum_{k_n > 0} \frac{2}{k_n^2 (H + H^2 k_n^2 + 1)} e^{-k_n^2 t / \tau_f} \right\} \quad (23)$$

The heating rate at the film / adherend interface can be calculated by differentiating equation 23 with respect to time, giving

$$\frac{dT}{dt}(0, t) = \frac{\bar{Q}_T}{\hat{\rho}\hat{c}_p} H \tau_f \left\{ \frac{1/\tau_f}{1+H} - \sum_{k_n > 0} \frac{-2k_n^2/\tau_f}{k_n^2 (H + H^2 k_n^2 + 1)} e^{-k_n^2 t / \tau_f} \right\} \quad (24)$$

or

$$\frac{dT}{dt}(0, t) = \frac{\bar{Q}_T}{\hat{\rho}\hat{c}_p} \left\{ \frac{H}{1+H} + \sum_{k_n > 0} \frac{2H}{(H + H^2 k_n^2 + 1)} e^{-k_n^2 t / \tau_f} \right\} \quad (25)$$

Using equation 10, we can write the reduced heating rate for the case of the semi-infinite adherend as

$$R_{\text{rate}} = \frac{H}{1+H} + \sum_{k_n > 0} \frac{2H}{(H + H^2 k_n^2 + 1)} e^{-k_n^2 t / \tau_f} \quad (26)$$

Figure 4 shows R_{rate} as a function of reduced time t/τ_f and H , calculated using equation 26 (summing to 500 roots using Mathematica®). Note that smaller values of H cause a greater reduction in heating rate, and that at long times the reduced heating rate approaches a constant value. Figure 5 superimposes the general solution on top of the solution for a semi-infinite thickness adherend, equation 19, and a finite thickness infinite conductivity adherend, equation 11. To make the comparison with the semi-infinite adherend, we utilize the transformation

$$\tau_i = H^2 \tau_f \quad (27)$$

to calculate R_{rate} in equation 19 as a function of τ_f and H . For small times, $t < 0.1\tau_i$, the general solution matches the semi-infinite thickness solution. For large times, $t > \tau_i$, the general solution matches the infinite conductivity solution. These observations show that the semi-infinite thickness solution is the short time model of the general problem, while the infinite conductivity model is the long time model of the general problem.




Figure 4. Reduced Heating Rate as a Function of t/τ_f and H for Finite Adherend Solution.

3. Calculations

In this section we perform heating rate calculations, using the models derived in section 2, for specific, likely adherend materials and thicknesses and likely film materials and thicknesses. The applicability of each result is discussed in more detail in section 4.1.

3.1 Material Properties. For our induction bonding application, the volumetrically heating film is a particulate composite composed of magnetic particles dispersed in a polymer matrix. The thermophysical properties of this film can be calculated from the component material properties using a simple volume averaging approach

$$\hat{\rho} = v_f \rho + (1 - v_f) \tilde{\rho} \quad (28)$$

$$\hat{c}_p = v_f c_p + (1 - v_f) \tilde{c}_p \quad (29)$$

where v_f is the particle volume fraction, ρ and c_p are particle properties, and $\tilde{\rho}$ and \tilde{c}_p are matrix properties. Since we have assumed uniform temperature in the film, the film conductivity and thermal diffusivity are not relevant. For specific calculations, we will use a promising material system identified by Wetzel and Fink [1] which contains 15% by volume nickel zinc ferrite.




Figure 5. Reduced Heating Rate as a Function of t/τ_f and H for Finite Adherend Solution, with Superimposed Semi-Infinite Thickness Adherend Model and Infinite Conductivity Solution.

Table 1. Film Component and Composite Material Properties. Polymer properties are typical for engineering thermoplastics and adhesives. Nickel zinc ferrite properties from Snelling [5]. Film properties calculated using equations 28 and 29 with a particle volume fraction of $v_f = 15\%$.

	Polymer	NiZn Ferrite	Composite Film
Density, $\hat{\rho}$ (kg/m ³)	1000	4500	1525
Specific Heat, \hat{c}_p (J/kg K)	1000	750	963

Table 2. Adherend Thermophysical Properties. Polymer composite properties typical for engineering polymers. Ceramic properties (alumina) from Sheppard [6]. Metal properties (aluminum) from Ozisik [7].

	Composite	Ceramic	Metal
Density, ρ (kg/m ³)	1000	3900	2700
Specific heat, c_p (J/kg K)	1000	1000	900
Thermal conductivity, k (W/m K)	0.2	30	200
Thermal diffusivity, $\alpha \equiv k/\rho c_p$ (m ² /s)	2.0×10^{-7}	7.7×10^{-6}	8.2×10^{-5}

Table 1 gives the material properties for the individual components and the 15% particulate composite film.

The range of potential adherend materials used in applications includes polymer composite, ceramic, and metal. For composite materials, we will use the typical polymer material properties given in Table 2. Steel and aluminum are both candidate metal materials for armor applications. We will use aluminum properties for our representative metal adherend, as its higher thermal conductivity will provide a more extreme bound on possible adherend thermal loss effects. The aluminum thermophysical properties are given in Table 2. Two common ceramics used in armor applications are alumina and silicon carbide. The density and heat capacity of these materials are similar, but their thermal conductivities vary by an order of magnitude, with a value of ~ 30 W/m K for alumina and 270 W/m K for silicon carbide. We will use alumina as our model ceramic, since it provides a more intermediate value between the cases of metal and polymeric composite. However, the reader is cautioned to check material properties carefully before using the results calculated in later sections, as the high thermal conductivity of some ceramics may make them closer to our representative "metal" material properties than to our "ceramic" material properties. The full alumina thermophysical properties are given in Table 2.




Figure 6. Reduced Heating Rate as a Function of Film Thickness Ratio l/L for Various Adherend Materials and Infinite Conductivity Adherend Solution.

3.2 Bondline Heating Rates for Specific Material Systems.

3.2.1 Infinite Conductivity Adherend. Equation 11 predicts the reduced heating rate for a film in contact with an adherend with infinite conductivity. Using this model, Figure 6 shows R_{rate} as a function of film thickness ratio l/L for each adherend material in Table 2. Note that a ceramic adherend reduces the heating rate more than an aluminum adherend of identical thickness. This result occurs because, if the adherend is assumed to be at uniform temperature, thermal conductivity is no longer a relevant physical parameter. The reduction in heating rates is caused completely by heat capacity effects, and for our material properties the ceramic has a higher heat capacity than the aluminum. The plots also show that for film thickness ratios between 0.01 and 0.1, the adherend will reduce the insulated film heating rate by a factor of 10 to 100.

3.2.2 Semi-Infinite Thickness Adherend. Equation 19 predicts the reduced heating rate for a film in contact with an adherend with semi-infinite thickness. Unlike the infinite conductivity results of section 3.2.2, we cannot define a thickness ratio since the adherend thickness is not finite. Therefore, for adherend material studies, we are forced to calculate reduced heating




Figure 7. Reduced Heating Rate as a Function of Time and Film Thickness for Various Adherend Materials and Semi-Infinite Adherend Solution.

rates for specific film thicknesses. Equation 19 also shows that the reduced heating rate is a function of time. Figure 7 shows reduced heating rate as a function of film thickness and time, for the adherend materials of Table 2. The same data is presented in Figure 8, but allows easier interpretation as time for heating rate to be reduced to a given R_{rate} as a function of film thickness. Note that for a low conductivity adherend, such as a polymer composite, the heating rate will be reduced by a factor of 10 in under a minute, and by as much as 100 after a few minutes. For higher conductivity materials, such as aluminum, the thermal loss is more severe, reducing the heating rate to 1/1000 of its insulated value in under one minute. However, as will be discussed in section 4.1, these results are only applicable to high conductivity materials such as aluminum if the adherend is extremely thick.

3.2.3 Finite Thickness, Finite Conductivity Adherend. Equation 26 predicts the reduced heating rate for a film in contact with an adherend with finite thickness and finite conductivity. Figures 9 – 11 show the reduced heating rate as a function of time and adherend thickness, for film thicknesses of 0.1 mm, 1 mm, and 5 mm, respectively. The adherend material properties are given by Table 2, and equation 26 is implemented by summing to 500 roots using Mathematica®.




Figure 8. Time to Achieve Reduced Heating Rates as a Function of Film Thickness for Various Adherend Materials and Semi-Infinite Adherend Solution.




Figure 9. Reduced Heating Rate as a Function of Time and Adherend Thickness for Various Adherend Materials, with 0.1 mm Film Thickness and Finite Adherend Solution.




Figure 10. Reduced Heating Rate as a Function of Time and Adherend Thickness for Various Adherend Materials, with 1 mm Film Thickness and Finite Adherend Solution.




Figure 11. Reduced Heating Rate as a Function of Time and Adherend Thickness for Various Adherend Materials, with 5 mm Film Thickness and Finite Adherend Solution.

First consider the case of a 0.1 mm film thickness, Figure 9. The adherend thicknesses shown, 5 mm, 1 cm, and 2 cm, are relatively thin adherends since the film thickness is also thin. For the aluminum and ceramic cases, note that the heating rate drops to the infinite conductivity solution value within seconds. For a 5 mm thick adherend, the heating rate is reduced by a factor of 100. For the thicker adherends, the heating rate reduction approaches a factor 1000. Note that in all cases the ceramic adherend results in a lower effective heating rate than the aluminum adherend. This behavior occurs because the adherends closely follow the infinite conductivity solution, which is governed by specific heat. For the thickest polymer adherend, 2 cm, the results closely follow the infinite adherend solution through 500 s. For the thinner adherends, the infinite conductivity solution is reached at large times, > 300 s. For all of the polymer adherend thicknesses, the heating rate is reduced by roughly a factor of 100.

Figure 10 shows the reduced heating rates for the case of a 1 mm film. The adherend thicknesses used are 5 mm, 1 cm, 2 cm, and 5 cm. The behavior is qualitatively similar to that of the 0.1 mm adherend, except that the heating rates are a factor of 10 greater. The aluminum and ceramic adherends reduce the heating rates by a factor of 10-100, while the polymer adherends reduce the heating rates by roughly a factor of 10. Again, ceramic adherends present a greater heat sink than the aluminum adherends.

Figure 11 shows the reduced heating rates for the case of a 5 mm film. Since this is a very thick film, the adherend thickness used are 2 cm, 5 cm, and 10 cm. Note that, because of the thickness of the polymer adherends, all cases obey the semi-infinite thickness model. The aluminum and ceramic adherends span the semi-infinite thickness and infinite conductivity solutions, depending on their thickness and the process time. Note that for the thicker adherends, initially the aluminum adherend presents a greater heat sink but at longer times the ceramic becomes a greater heat sink. The polymer adherends reduce the heating rates by up to a factor of 7, while the aluminum and ceramic adherends reduce the heating rates by a factor of 10-100.

4. Analysis and Conclusions

4.1 Model Applicability. In section 3.2 we calculated reduced heating rates for a variety of adherend materials using three different heat transfer models. The model used in section 3.2.3 is most general, and applies to any adherend with finite conductivity and thickness. The models of sections 3.2.1 and 3.2.2 are only applicable under conditions of infinite adherend conductivity and thickness, respectively. Since, in practice, we do not ever encounter adherends with truly infinite conductivity or thickness, we need to establish a criterion for

determining the applicability of these models to a given adherend. This criterion is the characteristic thermal conduction time.

We define the characteristic thermal conduction time for an adherend as

$$t_c = \frac{L^2}{\alpha} \quad (30)$$

Note that t_c is equivalent to τ_f defined by equation 21. t_c is roughly the amount of time required for a significant amount of thermal energy to transport the distance L in a material with thermal diffusivity α . For times much less than the characteristic thermal conduction time, $t \ll t_c$, significant thermal energy does not reach the insulated face of the adherend, so the semi-infinite adherend solution models the behavior accurately. For times much greater than the characteristic thermal conduction time, $t \gg t_c$, thermal diffusion occurs very rapidly, so the infinite adherend conductivity solution models the behavior accurately. If $t \sim t_c$, then only the general finite thickness, finite conductivity model will be accurate. These short-time, long-time solution relationships were shown graphically in Figure 5.

To evaluate model applicability for a specific adherend material and thickness, equation 30 should be used to calculate the characteristic conduction times. This approach provides a design tool for specific process prediction. For the purpose of general adherend material assessment, we will find it more appropriate to choose a characteristic processing time, and then calculate a characteristic conduction length. Based on equation 30, we define the characteristic thermal conduction length as

$$L_c = \sqrt{\alpha \cdot \text{process time}} \quad (31)$$

Thermal conduction length, for a given process time, is a material parameter independent of adherend thickness. If an adherend thickness is much less than its characteristic conduction length, $L \ll L_c$, then $t \gg t_c$ and the infinite conductivity solution applies. If an adherend thickness is much greater than its characteristic conduction length, $L \gg L_c$, then $t \ll t_c$ and the semi-infinite adherend solution applies. If $L \sim L_c$, then $t \sim t_c$ and only the general solution will predict accurate heating rates.

Table 3 gives characteristic thermal conduction lengths for each adherend material in Table 2 and for a typical process time of 100 s. Using these results, we can assess the applicability of each model to each adherend material. The infinite conductivity model is most applicable to the metal adherend, and should be accurate for adherend thicknesses much less than 9 cm. For structural metal and light armor, with a thickness of only a few centimeters, this assumption

Table 3. Adherend Characteristic Conduction Lengths, as defined by equation 31, for a process time of 100 s.

	Composite	Ceramic	Metal
Char. conduction length	4.47 mm	2.8 cm	9.1 cm

should be accurate. The semi-infinite adherend thickness model is most applicable to the composite adherend, which has a low thermal conductivity and an L_c of only 4 mm. For a typical 1 or 2 cm composite structural or armor panel, this model should prove accurate. The thermal conduction length of the alumina ceramic is 3 cm, which is very close to the actual ceramic tile armor dimensions. Therefore it is most likely that the finite thickness, finite conductivity approach is the only model which will give accurate results for ceramic armor adherends.

4.2 Effect of Adherends on Feasibility of Bonding with Magnetic Particle Films.

Wetzel and Fink [1] have performed a feasibility study for bonding with magnetic particle films, considering both thermoplastic hot-melt bonding and elevated temperature adhesive bonding. Typical thermoplastic hot-melt bonding requires high temperatures (250–400°C) to ensure bond integrity but short process times (under 1 minute at processing temperature) to prevent thermal degradation [8]. This processing requires film heating rates of 10 – 100°C/s. Elevated temperature accelerated adhesive bonds, which involve lower processing temperatures (100 – 180°C) and longer process times (5 - 20 minutes), only require heating rates of 1 – 10°C/s.

Wetzel and Fink [1] also provide predictions of heating rates for insulated magnetic particle films with no adherends. As a benchmark, we will use a 15% NiZn ferrite / polymer film. From Wetzel and Fink [1], the expected heating rates for an insulated film of this composition are given in Table 4 for field frequencies of 100 kHz, 1 MHz, and 10 MHz. Also shown in the table are the heating rates expected if the film is sandwiched between two identical adherends of various materials. A typical film thickness of 1 mm (half film thickness $l = 0.5$ mm) and adherend thickness of 2 cm are used for the calculations, and heating rate reductions are calculated using the finite thickness model of section 2.3.

These heating rates results show that thermoplastic hot-melt bonding is marginally feasible with all adherends at high frequencies (10 MHz), and still feasible with thick composite adherends at moderate (1 MHz) frequencies. For elevated temperature adhesive bonding, composite adherends should be feasible even at low (100 kHz) frequencies, while metal and ceramic adherends should be feasible at higher (> 1 MHz) frequencies.

Table 4. Expected Heating Rates for 15% NiZn Ferrite / Polymer Film with Thickness $2l = 1$ mm Sandwiched Between Two Identical Adherends of Various Materials.

Frequency	10 kHz	1 MHz	10 MHz
No adherend (insulated)	12 °C/s	120 °C/s	1200 °C/s
2 cm composite (after 1 minute)	1.2 °C/s	12 °C/s	120 °C/s
2 cm composite (after 5 minutes)	0.6 °C/s	6 °C/s	60 °C/s
2 cm ceramic	0.12 °C/s	1.2 °C/s	12 °C/s
2 cm aluminum	0.18 °C/s	1.8 °C/s	18 °C/s

The specific results presented in this section and in Table 4 are, of course, very limited. Only a few very specific adherend and film materials and thicknesses were taken into consideration. Additionally, the insulated film heating rates predicted in Wetzel and Fink [1] are only expected to be accurate to within one or two orders of magnitude. For more specific bonding design guidance, calculations should be performed for the materials and geometry under consideration, and experimentally measured film heat generation rates. However, these results do confirm the general feasibility of using magnetic particle films for bonding structural and armor components of various materials, including ceramics, metals, and polymer matrix composites.

4.3 Extension of Results to Non-Symmetric Adherends. The results derived in this report are strictly applicable to symmetric adherends only. That is, only bonding of two identical adherends (both in thickness and material properties) can be modeled. However, many magnetic particle film bonds will be performed on unsymmetric adherends. Examples include ceramic-composite bonds in multi-functional armor and metal-composite bonds for steel-framed composite shell vehicles. The solutions from this report certainly provide bounds on heating rates. A composite to ceramic bond will behave somewhere between a composite-composite and a ceramic-ceramic bond. Deriving a full, general, unsymmetric solution is possible but will be mathematically difficult. Wetzel [9] provides closely related solutions, for the case of negligible film thermal mass. A much simpler approach is to numerically solve for specific non-symmetric adherend cases, using for example a finite difference solution. It may also be possible to demonstrate a simple empirical rule for unsymmetric adherends based on the symmetric adherend solutions. For example, calculating R_{rate} independently for each adherend using the symmetric adherend solution and then using some sort of averaging approach to estimate the unsymmetric adherend solution. The investigation of unsymmetric adherends remains a topic for future investigation.

INTENTIONALLY LEFT BLANK.

5. References

1. Wetzel, E. D., and B. K. Fink. "Feasibility of Magnetic Particle Films for Curie Temperature- Controlled Processing of Composite Materials." ARL-TR-XX, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, to be published.
2. Trankle, E. "Die Losung Eines Speziellen Warmeleitungsproblems und Ihre Anwendung auf Analoge Physikalische Probleme." *Frequenz*, vol. 8, pp. 334-338, 1954.
3. Carslaw, H. S., and J. C. Jaeger, editors. *Conduction of Heat in Solids*. Oxford, UK: Clarendon Press, 1959, p. 306.
4. Carslaw, H. S., and J. C. Jaeger, editors. *Conduction of Heat in Solids*. Oxford, UK: Clarendon Press, 1959, p. 128.
5. Snelling, E. C. *Soft Ferrites: Properties and Applications*. London: ILIFFE Books Ltd., 1969.
6. Sheppard, L. M., editor. *Ceramic Source 1991-1992*. Westerville, OH: American Ceramic Society, Inc., 1991.
7. Ozisik, M. N. *Heat Transfer: A Basic Approach*. New York: McGraw Hill, 1985.
8. Fink, B. K., J. W. Gillespie, and N. Ersoy. "Thermal Degradation Effects on Consolidation and Bonding in the Thermoplastic Fiber Placement Process." ARL-TR-XX, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, to be published.
9. Wetzel, E. D. "Assessment of Heating Techniques for Metal-to-Composite Bonding in Infrastructure Rehabilitation." Technical Report 95-13, University of Delaware Center for Composite Materials, Newark, DE, 1995.

INTENTIONALLY LEFT BLANK.

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	DEFENSE TECHNICAL INFORMATION CENTER DTIC OCA 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218
1	HQDA DAMO FDT 400 ARMY PENTAGON WASHINGTON DC 20310-0460
1	OSD OUSD(A&T)/ODDR&E(R) DR R J TREW 3800 DEFENSE PENTAGON WASHINGTON DC 20301-3800
1	COMMANDING GENERAL US ARMY MATERIEL CMD AMCRDA TF 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	INST FOR ADVNCD TCHNLGY THE UNIV OF TEXAS AT AUSTIN 3925 W BRAKER LN STE 400 AUSTIN TX 78759-5316
1	DARPA SPECIAL PROJECTS OFFICE J CARLINI 3701 N FAIRFAX DR ARLINGTON VA 22203-1714
1	US MILITARY ACADEMY MATH SCI CTR EXCELLENCE MADN MATH MAJ HUBER THAYER HALL WEST POINT NY 10996-1786
1	DIRECTOR US ARMY RESEARCH LAB AMSRL D DR D SMITH 2800 POWDER MILL RD ADELPHI MD 20783-1197

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIRECTOR US ARMY RESEARCH LAB AMSRL CI AI R 2800 POWDER MILL RD ADELPHI MD 20783-1197
3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI LL 2800 POWDER MILL RD ADELPHI MD 20783-1197
3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI AP 2800 POWDER MILL RD ADELPHI MD 20783-1197
	<u>ABERDEEN PROVING GROUND</u>
2	DIR USARL AMSRL CI LP (BLDG 305)

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIRECTOR US ARMY RESEARCH LAB AMSRL CP CA D SNIDER 2800 POWDER MILL RD ADELPHI MD 20783-1145
1	DIRECTOR US ARMY RESEARCH LAB AMSRL OP SD TA 2800 POWDER MILL RD ADELPHI MD 20783-1145
3	DIRECTOR US ARMY RESEARCH LAB AMSRL OP SD TL 2800 POWDER MILL RD ADELPHI MD 20783-1145
1	DIRECTOR US ARMY RESEARCH LAB AMSRL OP SD TP 2800 POWDER MILL RD ADELPHI MD 20783-1145
1	DIRECTOR DA OASARDA SARD SO 103 ARMY PENTAGON WASHINGTON DC 20310-0103
1	DPTY ASST SECY FOR R&T SARD TT THE PENTAGON RM 3EA79 WASHINGTON DC 20301-7100
1	COMMANDER US ARMY MATERIEL CMD AMXMI INT 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
4	COMMANDER US ARMY ARDEC AMSTA AR CC G PAYNE J GEHBAUER C BAULIEU H OPAT PICATINNY ARSENAL NJ 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	COMMANDER US ARMY ARDEC AMSTA AR AE WW E BAKER J PEARSON PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR TD C SPINELLI PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR FSE PICATINNY ARSENAL NJ 07806-5000
6	COMMANDER US ARMY ARDEC AMSTA AR CCH A W ANDREWS S MUSALLI R CARR M LUCIANO E LOGSDEN T LOUZEIRO PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR CCH P J LUTZ PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR FSF T C LIVECCHIA PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR QAC T C C PATEL PICATINNY ARSENAL NJ 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	COMMANDER US ARMY ARDEC AMSTA AR M D DEMELLA PICATINNY ARSENAL NJ 07806-5000
3	COMMANDER US ARMY ARDEC AMSTA AR FSA A WARNASH B MACHAK M CHIEFA PICATINNY ARSENAL NJ 07806-5000
2	COMMANDER US ARMY ARDEC AMSTA AR FSP G M SCHIKSNIS D CARLUCCI PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR FSP A P KISATSKY PICATINNY ARSENAL NJ 07806-5000
2	COMMANDER US ARMY ARDEC AMSTA AR CCH C H CHANIN S CHICO PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA ASF PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR WET T SACHAR BLDG 172 PICATINNY ARSENAL NJ 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
9	COMMANDER US ARMY ARDEC AMSTA AR CCH B P DONADIA F DONLON P VALENTI C KNUTSON G EUSTICE S PATEL G WAGNECZ R SAYER F CHANG PICATINNY ARSENAL NJ 07806-5000
6	COMMANDER US ARMY ARDEC AMSTA AR CCL F PUZYCKI R MCHUGH D CONWAY E JAROSZEWSKI R SCHLENNER M CLUNE PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR QAC T D RIGOGLIOSO PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR SRE D YEE PICATINNY ARSENAL NJ 07806-5000
1	US ARMY ARDEC INTELLIGENCE SPECIALIST AMSTA AR WEL F M GUERRIERE PICATINNY ARSENAL NJ 07806-5000
2	PEO FIELD ARTILLERY SYS SFAE FAS PM H GOLDMAN T MCWILLIAMS PICATINNY ARSENAL NJ 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
11	PM TMAS SFAE GSSC TMA R MORRIS C KIMKER D GUZOWICZ E KOPACZ R ROESER R DARCY R MCDANOLDS L D ULISSE C ROLLER J MCGREEN B PATTEN PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR WEA J BRESCIA PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC PRODUCTION BASE MODERN ACTY AMSMC PBM K PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY TACOM PM ABRAMS SFAE ASM AB 6501 ELEVEN MILE RD WARREN MI 48397-5000
6	PM SADARM SFAE GCSS SD COL B ELLIS M DEVINE R KOWALSKI W DEMASSI J PRITCHARD S HROWNAK PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY TACOM AMSTA SF WARREN MI 48397-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
3	COMMANDER US ARMY TACOM PM TACTICAL VEHICLES SFAE TVL SFAE TVM SFAE TVH 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM BFVS SFAE ASM BV 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM AFAS SFAE ASM AF 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM RDT&E SFAE GCSS W AB J GODELL 6501 ELEVEN MILE RD WARREN MI 48397-5000
2	COMMANDER US ARMY TACOM PM SURV SYS SFAE ASM SS T DEAN SFAE GCSS W GSI M D COCHRAN 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	US ARMY CERL R LAMPO 2902 NEWMARK DR CHAMPAIGN IL 61822
1	COMMANDER US ARMY TACOM PM SURVIVABLE SYSTEMS SFAE GCSS W GSI H M RYZYI 6501 ELEVEN MILE RD WARREN MI 48397-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	COMMANDER US ARMY TACOM PM BFV SFAE GCSS W BV S DAVIS 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM LIGHT TACTICAL VHCLS AMSTA TR S A J MILLS MS 209 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM CHIEF ABRAMS TESTING SFAE GCSS W AB QT T KRASKIEWICZ 6501 ELEVEN MILE RD WARREN MI 48397-5000
15	COMMANDER US ARMY TACOM AMSTA TR R J CHAPIN R MCCLELLAND D THOMAS J BENNETT D HANSEN AMSTA JSK S GOODMAN J FLORENCE K IYER D TEMPLETON A SCHUMACHER AMSTA TR D D OSTBERG L HINOJOSA B RAJU AMSTA CS SF H HUTCHINSON F SCHWARZ WARREN MI 48397-5000
1	COMMANDER WATERVLIET ARSENAL SMCWV QAE Q B VANINA BLDG 44 WATERVLIET NY 12189-4050

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	COMMANDER WATERVLIET ARSENAL SMCWV SPM T MCCLOSKEY BLDG 253 WATERVLIET NY 12189-4050
2	TSM ABRAMS ATZK TS S JABURG W MEINSHAUSEN FT KNOX KY 40121
3	ARMOR SCHOOL ATZK TD R BAUEN J BERG A POMEY FT KNOX KY 40121
11	BENET LABORATORIES AMSTA AR CCB R FISCELLA G D ANDREA E KATHE M SCAVULO G SPENCER P WHEELER K MINER J VASILAKIS G FRIAR R HASENBEIN AMSTA CCB R S SOPOK WATERVLIET NY 12189-4050
2	HQ IOC TANK AMMUNITION TEAM AMSIO SMT R CRAWFORD W HARRIS ROCK ISLAND IL 61299-6000
2	DAVID TAYLOR RESEARCH CTR R ROCKWELL W PHYLLAIER BETHESDA MD 20054-5000
2	COMMANDER US ARMY AMCOM AVIATION APPLIED TECH DIR J SCHUCK FT EUSTIS VA 23604-5577

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIRECTOR US ARMY AMCOM SFAE AV RAM TV D CALDWELL BLDG 5300 REDSTONE ARSENAL AL 35898	1	NAVAL SURFACE WARFARE CTR DAHLGREN DIV CODE G06 DAHLGREN VA 22448
2	US ARMY CORPS OF ENGINEERS CERD C T LIU CEW ET T TAN 20 MASS AVE NW WASHINGTON DC 20314	1	NAVAL SURFACE WARFARE CTR TECH LIBRARY CODE 323 17320 DAHLGREN RD DAHLGREN VA 22448
1	US ARMY COLD REGIONS RSCH & ENGRNG LAB P DUTTA 72 LYME RD HANOVER NH 03755	1	NAVAL SURFACE WARFARE CTR CRANE DIVISION M JOHNSON CODE 20H4 LOUISVILLE KY 40214-5245
1	SYSTEM MANAGER ABRAMS ATZK TS LTC J H NUNN BLDG 1002 RM 110 FT KNOX KY 40121	8	DIRECTOR US ARMY NATIONAL GROUND INTELLIGENCE CTR D LEITER M HOLTUS M WOLFE S MINGLEDORF J GASTON W GSTATTENBAUER R WARNER J CRIDER 220 SEVENTH ST NE CHARLOTTESVILLE VA 22091
1	USA SBCCOM PM SOLDIER SPT AMSSB PM RSS A J CONNORS KANSAS ST NATICK MA 01760-5057	6	US ARMY SBCCOM SOLDIER SYSTEMS CENTER BALLISTICS TEAM J WARD MARINE CORPS TEAM J MACKIEWICZ BUS AREA ADVOCACY TEAM W HASKELL SSCNC WST W NYKVIST T MERRILL S BEAUDOIN KANSAS ST NATICK MA 01760-5019
3	BALLISTICS TEAM AMSSB RIP PHIL CUNNIFF JOHN SONG WALTER ZUKAS KANSAS ST NATICK MA 01760-5057	3	NAVAL RESEARCH LAB I WOLOCK CODE 6383 R BADALIANE CODE 6304 L GAUSE WASHINGTON DC 20375
2	MATERIAL SCIENCE TEAM AMSSB RSS JEAN HERBERT MICHAEL SENNETT KANSAS ST NATICK MA 01760-5057	2	NAVAL SURFACE WARFARE CTR U SORATHIA C WILLIAMS CD 6551 9500 MACARTHUR BLVD WEST BETHESDA MD 20817
2	OFC OF NAVAL RESEARCH D SIEGEL CODE 351 J KELLY 800 N QUINCY ST ARLINGTON VA 22217-5660		

NO. OF
COPIES ORGANIZATION

9 US ARMY RESEARCH OFC
A CROWSON
J CHANDRA
H EVERETT
J PRATER
R SINGLETON
G ANDERSON
D STEPP
D KISEROW
J CHANG
PO BOX 12211
RESEARCH TRIANGLE PARK NC
27709-2211

2 COMMANDER
NAVAL SURFACE WARFARE CTR
CARDEROCK DIVISION
R PETERSON CODE 2020
M CRITCHFIELD CODE 1730
BETHESDA MD 20084

8 NAVAL SURFACE WARFARE CTR
J FRANCIS CODE G30
D WILSON CODE G32
R D COOPER CODE G32
J FRAYSSE CODE G33
E ROWE CODE G33
T DURAN CODE G33
L DE SIMONE CODE G33
R HUBBARD CODE G33
DAHLGREN VA 22448

1 NAVAL SEA SYSTEMS CMD
D LIESE
2531 JEFFERSON DAVIS HWY
ARLINGTON VA 22242-5160

1 NAVAL SURFACE WARFARE CTR
M LACY CODE B02
17320 DAHLGREN RD
DAHLGREN VA 22448

2 NAVAL SURFACE WARFARE CTR
CARDEROCK DIVISION
R CRANE CODE 2802
C WILLIAMS CODE 6553
3A LEGGETT CIR
BETHESDA MD 20054-5000

1 EXPEDITIONARY WARFARE DIV N85
F SHOUP
2000 NAVY PENTAGON
WASHINGTON DC 20350-2000

NO. OF
COPIES ORGANIZATION

1 AFRL MLBC
2941 P ST RM 136
WRIGHT PATTERSON AFB OH
45433-7750

1 AFRL MLSS
R THOMSON
2179 12TH ST RM 122
WRIGHT PATTERSON AFB OH
45433-7718

2 AFRL
F ABRAMS
J BROWN
BLDG 653
2977 P ST STE 6
WRIGHT PATTERSON AFB OH
45433-7739

1 AFRL MLS OL
L COULTER
7278 4TH ST
BLDG 100 BAY D
HILL AFB UT 84056-5205

1 OSD
JOINT CCD TEST FORCE
OSD JCCD
R WILLIAMS
3909 HALLS FERRY RD
VICKSBURG MS 29180-6199

1 DEFENSE NUCLEAR AGENCY
INNOVATIVE CONCEPTS DIV
6801 TELEGRAPH RD
ALEXANDRIA VA 22310-3398

1 WATERWAYS EXPERIMENT
D SCOTT
3909 HALLS FERRY RD SC C
VICKSBURG MS 39180

5 DIRECTOR
LLNL
R CHRISTENSEN
S DETERESA
F MAGNESS
M FINGER MS 313
M MURPHY L 282
PO BOX 808
LIVERMORE CA 94550

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
3	DARPA M VANFOSSEN S WAX L CHRISTODOULOU 3701 N FAIRFAX DR ARLINGTON VA 22203-1714	1	OAK RIDGE NATIONAL LABORATORY C EBERLE MS 8048 PO BOX 2008 OAK RIDGE TN 37831
2	FAA TECH CENTER P SHYPRYKEVICH AAR 431 ATLANTIC CITY NJ 08405	1	OAK RIDGE NATIONAL LABORATORY C D WARREN MS 8039 PO BOX 2008 OAK RIDGE TN 37831
2	SERDP PROGRAM OFC PM P2 C PELLERIN B SMITH 901 N STUART ST STE 303 ARLINGTON VA 22203	7	NIST R PARNAS J DUNKERS M VANLANDINGHAM MS 8621 J CHIN MS 8621 D HUNSTON MS 8543 J MARTIN MS 8621 D DUTHINH MS 8611 100 BUREAU DR GAITHERSBURG MD 20899
1	FAA MIL HDBK 17 CHAIR L ILCEWICZ 1601 LIND AVE SW ANM 115N RESTON VA 98055	1	HYDROGEOLOGIC INC SERDP ESTCP SPT OFC S WALSH 1155 HERNDON PKWY STE 900 HERNDON VA 20170
1	US DEPT OF ENERGY OFC OF ENVIRONMENTAL MANAGEMENT P RITZCOVAN 19901 GERMANTOWN RD GERMANTOWN MD 20874-1928	3	NASA LANGLEY RSCH CTR AMSRL VS W ELBER MS 266 F BARTLETT JR MS 266 G FARLEY MS 266 HAMPTON VA 23681-0001
1	DIRECTOR LLNL F ADESSIO MS B216 PO BOX 1633 LOS ALAMOS NM 87545	1	NASA LANGLEY RSCH CTR T GATES MS 188E HAMPTON VA 23661-3400
1	OAK RIDGE NATIONAL LABORATORY R M DAVIS PO BOX 2008 OAK RIDGE TN 37831-6195	1	FHWA E MUNLEY 6300 GEORGETOWN PIKE MCLEAN VA 22101
3	DIRECTOR SANDIA NATIONAL LABS APPLIED MECHANICS DEPT MS 9042 J HANDROCK Y R KAN J LAUFFER PO BOX 969 LIVERMORE CA 94551-0969	4	CYTEC FIBERITE R DUNNE D KOHLI M GILLIO R MAYHEW 1300 REVOLUTION ST HAVRE DE GRACE MD 21078

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	USDOT FEDERAL RAILRD M FATEH RDV 31 WASHINGTON DC 20590
1	CENTRAL INTLLGNC AGENCY OTI WDAG GT W L WALTMAN PO BOX 1925 WASHINGTON DC 20505
1	MARINE CORPS INTLLGNC ACTVTY D KOSITZKE 3300 RUSSELL RD STE 250 QUANTICO VA 22134-5011
1	DIRECTOR NATIONAL GRND INTLLGNC CTR IANG TMT 220 SEVENTH ST NE CHARLOTTESVILLE VA 22902-5396
1	DIRECTOR DEFENSE INTLLGNC AGENCY TA 5 K CRELLING WASHINGTON DC 20310
1	ADVANCED GLASS FIBER YARNS T COLLINS 281 SPRING RUN LANE STE A DOWNINGTON PA 19335
1	COMPOSITE MATERIALS INC D SHORTT 19105 63 AVE NE PO BOX 25 ARLINGTON WA 98223
1	JPS GLASS L CARTER PO BOX 260 SLATER RD SLATER SC 29683
1	COMPOSITE MATERIALS INC R HOLLAND 11 JEWEL CT ORINDA CA 94563
1	COMPOSITE MATERIALS INC C RILEY 14530 S ANSON AVE SANTA FE SPRINGS CA 90670

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	COMPOSIX D BLAKE L DIXON 120 O NEILL DR HEBRUN OH 43025
2	SIMULA J COLTMAN R HUYETT 10016 S 51ST ST PHOENIX AZ 85044
1	SIOUX MFG B KRIEL PO BOX 400 FT TOTTEN ND 58335
2	PROTECTION MATERIALS INC M MILLER F CRILLEY 14000 NW 58 CT MIAMI LAKES FL 33014
3	FOSTER MILLER J J GASSNER M ROYLANCE W ZUKAS 195 BEAR HILL RD WALTHAM MA 02354-1196
1	ROM DEVELOPMENT CORP R O MEARA 136 SWINEBURNE ROW BRICK MARKET PLACE NEWPORT RI 02840
2	TEXTRON SYSTEMS T FOLTZ M TREASURE 201 LOWELL ST WILMINGTON MA 08870-2941
1	GLCC INC J RAY 103 TRADE ZONE DR STE 26C WEST COLUMBIA SC 29170
1	O GARA HESS & EISENHARDT M GILLESPIE 9113 LESANT DR FAIRFIELD OH 45014

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	MILLIKEN RSCH CORP H KUHN M MACLEOD PO BOX 1926 SPARTANBURG SC 29303
1	CONNEAUGHT INDUSTRIES INC J SANTOS PO BOX 1425 COVENTRY RI 02816
2	BATTELLE NATICK OPNS J CONNORS B HALPIN 209 W CENTRAL ST STE 302 NATICK MA 01760
1	ARMTEC DEFENSE PRODUCTS S DYER 85 901 AVE 53 PO BOX 848 COACHELLA CA 92236
3	PACIFIC NORTHWEST LAB M SMITH G VAN ARSDALE R SHIPPELL PO BOX 999 RICHLAND WA 99352
8	ALLIANT TECHSYSTEMS INC C CANDLAND MN11 2830 C AAKHUS MN11 2830 B SEE MN11 2439 N VLAHAKUS MN11 2145 R DOHRN MN11 2830 S HAGLUND MN11 2439 M HISSONG MN11 2830 D KAMDAR MN11 2830 600 SECOND ST NE HOPKINS MN 55343-8367
2	AMOCO PERFORMANCE PRODUCTS M MICHNO JR J BANISAUKAS 4500 MCGINNIS FERRY RD ALPHARETTA GA 30202-3944
1	SAIC M PALMER 1410 SPRING HILL RD STE 400 MS SH4 5 MCLEAN VA 22102

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	SAIC G CHRYSSOMALLIS 3800 W 80TH ST STE 1090 BLOOMINGTON MN 55431
1	AAI CORPORATION T G STASTNY PO BOX 126 HUNT VALLEY MD 21030-0126
1	APPLIED COMPOSITES W GRISCH 333 NORTH SIXTH ST ST CHARLES IL 60174
3	ALLIANT TECHSYSTEMS INC J CONDON E LYNAM J GERHARD WV01 16 STATE RT 956 PO BOX 210 ROCKET CENTER WV 26726-0210
1	CUSTOM ANALYTICAL ENG SYS INC A ALEXANDER 13000 TENSOR LANE NE FLINTSTONE MD 21530
1	OFC DEPUTY UNDER SEC DEFNS JAMES THOMPSON 1745 JEFFERSON DAVIS HWY CRYSTAL SQ 4 STE 501 ARLINGTON VA 22202
1	PROJECTILE TECHNOLOGY INC 515 GILES ST HAVRE DE GRACE MD 21078
5	AEROJET GEN CORP D PILLASCH T COULTER C FLYNN D RUBAREZUL M GREINER 1100 WEST HOLLYVALE ST AZUSA CA 91702-0296
3	HEXCEL INC R BOE PO BOX 18748 SALT LAKE CITY UT 84118

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	HERCULES INC HERCULES PLAZA WILMINGTON DE 19894
1	BRIGS COMPANY J BACKOFEN 2668 PETERBOROUGH ST HERNDON VA 22071-2443
1	ZERNOW TECHNICAL SERVICES L ZERNOW 425 W BONITA AVE STE 208 SAN DIMAS CA 91773
2	OLIN CORPORATION FLINCHBAUGH DIV E STEINER B STEWART PO BOX 127 RED LION PA 17356
1	OLIN CORPORATION L WHITMORE 10101 NINTH ST NORTH ST PETERSBURG FL 33702
1	GKN AEROSPACE D OLDS 15 STERLING DR WALLINGFORD CT 06492
5	SIKORSKY AIRCRAFT G JACARUSO T CARSTENSAN B KAY S GARBO MS S330A J ADELMANN 6900 MAIN ST PO BOX 9729 STRATFORD CT 06497-9729
1	PRATT & WHITNEY C WATSON 400 MAIN ST MS 114 37 EAST HARTFORD CT 06108
1	AEROSPACE CORP G HAWKINS M4 945 2350 E EL SEGUNDO BLVD EL SEGUNDO CA 90245

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	CYTEC FIBERITE M LIN W WEB 1440 N KRAEMER BLVD ANAHEIM CA 92806
1	HEXCEL T BITZER 11711 DUBLIN BLVD DUBLIN CA 94568
1	BOEING R BOHLMANN PO BOX 516 MC 5021322 ST LOUIS MO 63166-0516
2	BOEING DFNSE & SPACE GP W HAMMOND S 4X55 J RUSSELL S 4X55 PO BOX 3707 SEATTLE WA 98124-2207
2	BOEING ROTORCRAFT P MINGURT P HANDEL 800 B PUTNAM BLVD WALLINGFORD PA 19086
1	BOEING DOUGLAS PRODUCTS DIV L J HART SMITH 3855 LAKEWOOD BLVD D800 0019 LONG BEACH CA 90846-0001
1	LOCKHEED MARTIN S REEVE 8650 COBB DR D 73 62 MZ 0648 MARIETTA GA 30063-0648
1	LOCKHEED MARTIN SKUNK WORKS D FORTNEY 1011 LOCKHEED WAY PALMDALE CA 93599-2502
1	LOCKHEED MARTIN R FIELDS 1195 IRWIN CT WINTER SPRINGS FL 32708

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	MATERIALS SCIENCES CORP B W ROSEN 500 OFC CENTER DR STE 250 FT WASHINGTON PA 19034	2	GDLS D REES M PASIK PO BOX 2074 WARREN MI 48090-2074
1	UDLP D MARTIN PO BOX 359 SANTA CLARA CA 95052	1	GDLS MUSKEGON OPERATIONS W SOMMERS JR 76 GETTY ST MUSKEGON MI 49442
1	NORTHROP GRUMMAN CORP ELECTRONIC SENSORS & SYSTEMS DIV E SCHOCH MS V 16 1745A W NURSERY RD LINTHICUM MD 21090	1	GENERAL DYNAMICS AMPHIBIOUS SYS SURVIVABILITY LEAD G WALKER 991 ANNAPOLIS WAY WOODBIDGE VA 22191
2	NORTHROP GRUMMAN ENVIRONMENTAL PROGRAMS R OSTERMAN A YEN 8900 E WASHINGTON BLVD PICO RIVERA CA 90660	6	INST FOR ADVANCED TECH H FAIR I MCNAB P SULLIVAN S BLESS W REINECKE C PERSAD 3925 W BRAKER LN STE 400 AUSTIN TX 78759-5316
1	UDLP G THOMAS PO BOX 58123 SANTA CLARA CA 95052	2	CIVIL ENGR RSCH FOUNDATION PRESIDENT H BERNSTEIN R BELLE 1015 15TH ST NW STE 600 WASHINGTON DC 20005
2	UDLP R BARRETT MAIL DROP M53 V HORVATICH MAIL DROP M53 328 W BROKAW RD SANTA CLARA CA 95052-0359	1	ARROW TECH ASSO 1233 SHELBURNE RD STE D8 SOUTH BURLINGTON VT 05403-7700
3	UDLP GROUND SYSTEMS DIVISION M PEDRAZZI MAIL DROP N09 A LEE MAIL DROP N11 M MACLEAN MAIL DROP N06 1205 COLEMAN AVE SANTA CLARA CA 95052	1	R EICHELBERGER CONSULTANT 409 W CATHERINE ST BEL AIR MD 21014-3613
4	UDLP R BRYNSVOLD P JANKE MS 170 4800 EAST RIVER RD MINNEAPOLIS MN 55421-1498	1	UCLA MANE DEPT ENGR IV H T HAHN LOS ANGELES CA 90024-1597
1	GDLS DIVISION D BARTLE PO BOX 1901 WARREN MI 48090		

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	UNIV OF DAYTON RESEARCH INST R Y KIM A K ROY 300 COLLEGE PARK AVE DAYTON OH 45469-0168
1	MIT P LAGACE 77 MASS AVE CAMBRIDGE MA 01887
1	IIT RESEARCH CENTER D ROSE 201 MILL ST ROME NY 13440-6916
1	GA TECH RSCH INST GA INST OF TCHNLGY P FRIEDERICH ATLANTA GA 30392
1	MICHIGAN ST UNIV MSM DEPT R AVERILL 3515 EB EAST LANSING MI 48824-1226
1	UNIV OF KENTUCKY L PENN 763 ANDERSON HALL LEXINGTON KY 40506-0046
1	UNIV OF WYOMING D ADAMS PO BOX 3295 LARAMIE WY 82071
2	PENN STATE UNIV R MCNITT C BAKIS 212 EARTH ENGR SCIENCES BLDG UNIVERSITY PARK PA 16802
1	PENN STATE UNIV R S ENGEL 245 HAMMOND BLDG UNIVERSITY PARK PA 16801
1	PURDUE UNIV SCHOOL OF AERO & ASTRO C T SUN W LAFAYETTE IN 47907-1282

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	STANFORD UNIV DEPT OF AERONAUTICS & AEROBALLISTICS S TSAI DURANT BLDG STANFORD CA 94305
1	UNIV OF DAYTON J M WHITNEY COLLEGE PARK AVE DAYTON OH 45469-0240
7	UNIV OF DELAWARE CTR FOR COMPOSITE MTRLS J GILLESPIE M SANTARE G PALMESE S YARLAGADDA S ADVANI D HEIDER D KUKICH 201 SPENCER LABORATORY NEWARK DE 19716
1	DEPT OF MATERIALS SCIENCE & ENGINEERING UNIVERSITY OF ILLINOIS AT URBANA CHAMPAIGN J ECONOMY 1304 WEST GREEN ST 115B URBANA IL 61801
1	NORTH CAROLINA STATE UNIV CIVIL ENGINEERING DEPT W RASDORF PO BOX 7908 RALEIGH NC 27696-7908
1	UNIV OF MARYLAND DEPT OF AEROSPACE ENGNRNG A J VIZZINI COLLEGE PARK MD 20742
3	UNIV OF TEXAS AT AUSTIN CTR FOR ELECTROMECHANICS J PRICE A WALLS J KITZMILLER 10100 BURNET RD AUSTIN TX 78758-4497

NO. OF COPIES	ORGANIZATION
3	VA POLYTECHNICAL INST & STATE UNIV DEPT OF ESM M W HYER K REIFSNIDER R JONES BLACKSBURG VA 24061-0219
1	DREXEL UNIV A S D WANG 32ND & CHESTNUT ST PHILADELPHIA PA 19104
1	SOUTHWEST RSCH INST ENGR & MATL SCIENCES DIV J RIEGEL 6220 CULEBRA RD PO DRAWER 28510 SAN ANTONIO TX 78228-0510
	<u>ABERDEEN PROVING GROUND</u>
1	US ARMY MATERIEL SYSTEMS ANALYSIS ACTIVITY P DIETZ 392 HOPKINS RD AMXSY TD APG MD 21005-5071
1	DIRECTOR US ARMY RESEARCH LAB AMSRL OP AP L APG MD 21005-5066
105	DIR USARL AMSRL CI AMSRL CI H W STUREK AMSRL CI S A MARK AMSRL CS IO FI M ADAMSON AMSRL SL B J SMITH AMSRL SL BA AMSRL SL BL D BELY R HENRY AMSRL SL BG AMSRL SL I AMSRL WM E SCHMIDT

NO. OF COPIES	ORGANIZATION
	<u>ABERDEEN PROVING GROUND (CONT)</u>
	AMSRL WM B A HORST AMSRL WM BA F BRANDON AMSRL WM BC P PLOSTINS D LYON J NEWILL S WILKERSON A ZIELINSKI AMSRL WM BD B FORCH R FIFER R PESCE RODRIGUEZ B RICE AMSRL WM BE C LEVERITT D KOOKER AMSRL WM BR C SHOEMAKER J BORNSTEIN AMSRL WM M D VIECHNICKI G HAGNAUER J MCCAULEY B TANNER AMSRL WM MA R SHUFORD P TOUCHET N BECK TAN AMSRL WM MA D FLANAGAN L GHIORSE D HARRIS S MCKNIGHT P MOY P PATTERSON G RODRIGUEZ A TEETS R YIN AMSRL WM MB B FINK J BENDER T BOGETTI R BOSSOLI L BURTON K BOYD S CORNELISON P DEHMER R DOOLEY W DRYSDALE G GAZONAS

NO. OF
COPIES

ORGANIZATION

ABERDEEN PROVING GROUND (CONT)

AMSRL WM MB
S GHIORSE
D GRANVILLE
D HOPKINS
C HOPPEL
D HENRY
R KASTE
M KLUSEWITZ
M LEADORE
R LIEB
E RIGAS
J SANDS
D SPAGNUOLO
W SPURGEON
J TZENG
E WETZEL
AMSRL WM MB
A FRYDMAN
AMRSL WM MC
J BEATTY
E CHIN
J MONTGOMERY
A WERECZCAK
J LASALVIA
J WELLS
AMSRL WM MD
W ROY
S WALSH
AMSRL WM T
B BURNS
AMSRL WM TA
W GILLICH
T HAVEL
J RUNYEON
M BURKINS
E HORWATH
B GOOCH
W BRUCHEY
AMSRL WM TC
R COATES
AMSRL WM TD
A DAS GUPTA
T HADUCH
T MOYNIHAN
F GREGORY
A RAJENDRAN
M RAFTENBERG
M BOTELER
T WEERASOORIYA
D DANDEKAR
A DIETRICH

NO. OF
COPIES

ORGANIZATION

ABERDEEN PROVING GROUND (CONT)

AMSRL WM TE
A NILLER
J POWELL
AMSRL SS SD
H WALLACE
AMSRL SS SE R
R CHASE
AMSRL SS SE DS
R REYZER
R ATKINSON
AMSRL SE L
R WEINRAUB
J DESMOND
D WOODBURY

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	LTD R MARTIN MERL TAMWORTH RD HERTFORD SG13 7DG UK	1	ISRAEL INST OF TECHNOLOGY S BODNER FACULTY OF MECHANICAL ENGR HAIFA 3200 ISRAEL
1	SMC SCOTLAND P W LAY DERA ROSYTH ROSYTH ROYAL DOCKYARD DUNFERMLINE FIFE KY 11 2XR UK	1	DSTO MATERIALS RESEARCH LAB NAVAL PLATFORM VULNERABILITY SHIP STRUCTURES & MTRLS DIV N BURMAN PO BOX 50 ASCOT VALE VICTORIA AUSTRALIA 3032
1	CIVIL AVIATION ADMINISTRATION T GOTTESMAN PO BOX 8 BEN GURION INTERNL AIRPORT LOD 70150 ISRAEL	1	ECOLE ROYAL MILITAIRE E CELENS AVE DE LA RENAISSANCE 30 1040 BRUXELLE BELGIQUE
1	AEROSPATIALE S ANDRE A BTE CC RTE MD132 316 ROUTE DE BAYONNE TOULOUSE 31060 FRANCE	1	DEF RES ESTABLISHMENT VALCARTIER A DUPUIS 2459 BOULEVARD PIE XI NORTH VALCARTIER QUEBEC CANADA PO BOX 8800 COURCELETTE GOA IRO QUEBEC CANADA
3	DRA FORT HALSTEAD P N JONES M HINTON SEVEN OAKS KENT TN 147BP UK	1	INSTITUT FRANCO ALLEMAND DE RECHERCHES DE SAINT LOUIS DE M GIRAUD 5 RUE DU GENERAL CASSAGNOU BOITE POSTALE 34 F 68301 SAINT LOUIS CEDEX FRANCE
1	DEFENSE RESEARCH ESTAB VALCARTIER F LESAGE COURCELETTE QUEBEC COA IRO CANADA	1	ECOLE POLYTECH J MANSON DMX LTC CH 1015 LAUSANNE SWITZERLAND
1	SWISS FEDERAL ARMAMENTS WKS W LANZ ALLMENDSTRASSE 86 3602 THUN SWITZERLAND	1	TNO PRINS MAURITS LABORATORY R IJSSELSTEIN LANGE KLEIWEG 137 PO BOX 45 2280 AA RIJSWIJK THE NETHERLANDS

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	FOA NATL DEFENSE RESEARCH ESTAB DIR DEPT OF WEAPONS & PROTECTION B JANZON R HOLMLIN S 172 90 STOCKHOLM SWEDEN
2	DEFENSE TECH & PROC AGENCY GROUND I CREWTHERR GENERAL HERZOG HAUS 3602 THUN SWITZERLAND
1	MINISTRY OF DEFENCE RAFAEL ARMAMENT DEVELOPMENT AUTH M MAYSELESS PO BOX 2250 HAIFA 31021 ISRAEL
1	DYNAMEC RESEARCH AB AKE PERSSON BOX 201 SE 151 23 SODERTALJE SWEDEN
1	TNO DEFENSE RESEARCH I H PASMAN POSTBUS 6006 2600 JA DELFT THE NETHERLANDS
1	B HIRSCH TACHKEMONY ST 6 NETAMUA 42611 ISRAEL
1	DEUTSCHE AEROSPACE AG DYNAMICS SYSTEMS M HELD PO BOX 1340 D 86523 SCHROBENHAUSEN GERMANY

INTENTIONALLY LEFT BLANK.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project(0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE April 2001		3. REPORT TYPE AND DATES COVERED Final, September 1998–December 1998
4. TITLE AND SUBTITLE Adherend Thermal Effects During Bonding With Inductively Heated Films			5. FUNDING NUMBERS AH42	
6. AUTHOR(S) Eric D. Wetzel and Bruce K. Fink				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-MB Aberdeen Proving Ground, MD 21005-5069			8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-2461	
9. SPONSORING/MONITORING AGENCY NAMES(S) AND ADDRESS(ES)			10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT(Maximum 200 words) The thermal performance of an inductively heated film sandwiched between two identical adherends is investigated. Models for infinite conductivity finite thickness adherends, finite conductivity semi-infinite thickness adherends, and finite conductivity finite thickness adherends are presented. Calculations are performed for polymer-matrix composite, ceramic, and metal adherends for a variety of adherend thicknesses. The results show that for expected bonding applications, film heating rates will be reduced by a factor of 10–100, as compared with insulated film heating rates with no attached adherends. Higher reductions in heating performance are noted for ceramic and metal adherends as compared with composite adherends. However, even with the most severe reductions in heating rates, bonding with inductively heated films is feasible.				
14. SUBJECT TERMS composite material, heat transfer, induction, adhesives			15. NUMBER OF PAGES 44	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED		18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED		19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED
				20. LIMITATION OF ABSTRACT UL

INTENTIONALLY LEFT BLANK.

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-2461 (Wetzel) Date of Report April 2001
2. Date Report Received _____
3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)
(DO NOT STAPLE)

DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

BUSINESS REPLY MAIL

FIRST CLASS PERMIT NO 0001,APG,MD

POSTAGE WILL BE PAID BY ADDRESSEE

DIRECTOR
US ARMY RESEARCH LABORATORY
ATTN AMSRL WM MB
ABERDEEN PROVING GROUND MD 21005-5069



NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

